



TREED FILAMENT DATASHEET

MATERIAL: Gonzales High Speed PLA

WE CARE ABOUT YOUR PRINTS

Suggested printing specs.	Value	Unit	Standard
Extruder Temperature	200° +/-10°	°C	Internal
Bed Temperature	cold to 80°	°C	Internal
Print speed	up to 200	mm/s	Internal
Fan	20-100	%	Internal
Minimum Nozzle Diameter	0,35	mm	Internal
Material Properties	Value	Unit	Standard
Density	1.24	g/cm ³	ASTM D792
Tensile Modulus	65.5	MPa	ASTM D882
Vicat Point	55-60	°C	ASTM3418
Melting Point	144°	°C	ASTM D3418

DISCLAIMER

The Information presented herein has been compiled from sources considered to be dependable and is accurate to the best of our knowledge. However, since data, safety standards, and government regulations are subject to change and the conditions of handling and use, or misuse, are beyond our control, Sa2p/Treed Filaments makes no warranty expressed or implied, with respect to completeness or continuing accuracy of the information contained herein and disclaims all liability for reliance thereon.

User should satisfy himself that he has all current data relevant to his particular use.